

## NZAC00780 Dulux Acratex 951 Coventry Coarse Sand Finish on New EIFS (Poly) [Exterior]

### Scope of Works

DULUX AcraTex 951 Tuscany Coarse is a high build acrylic based coating, formulated on 100% pure acrylic emulsions, inert mineral fillers, graded aggregates, fungicides and colour stable pigments.

### Substrate and Substrate Preparation

#### Substrate Notes

##### EXTERIOR INSULATION AND FINISHING SYSTEM

EPS (expanded polystyrene), XPS (extruded polystyrene) and/or ICF (insulating concrete formwork) substrates are lightweight cladding materials. Polystyrene is a lightweight, durable polymer that is manufactured in a number of grades depending on the application. In building situations, the lightweight characteristic is a major advantage in providing structural design economies. These materials also provide excellent thermal insulation. They have been used throughout the world for over 40 years in an extremely wide range of applications.

An EIFS coating system generally consists of a base coat (including imbedded mesh), cementitious render and primer or primer and acrylic render, followed by a high build topcoat.

#### Substrate Preparation Notes

Only a Dulux approved applicator can install a Exsulite EIFS cladding system, following the Installation Manual. Install other EIFS according to the manufactures instructions.

### Coating System Summary

- 1st Coat Specialized Construction Products Coarse Mesh Coat
- 2nd Coat Dulux Acratex Green Render Sealer
- 3rd Coat Dulux Acratex 951 Coventry Coarse Sand Finish
- 4th Coat Dulux Acratex AcraShield Advance Matt

### Coating System

#### 1st Coat — Specialized Construction Products Coarse Mesh Coat

Coat Type  
**1st Coat**

Datasheet  
**NZSP00023 Specialized Construction Products Coarse Mesh Coat**

Read the full Datasheet details at [Specialized Construction Products Coarse Mesh Coat](#)

#### Application Methods



**Trowel**

	Min	Max	Recommended
Wet Film Per Coat (microns)	<b>3000</b>	<b>4000</b>	
Dry Film Per Coat (microns)	<b>3000</b>	<b>4000</b>	
Recoat Time **	<b>8 Hours</b>	<b>Indefinite</b>	

V.O.C. Level  
**<1 g/L**

Meets ECNZ V.O.C. Requirements?  
**Not Applicable**

#### Coating Application Details

MIXING: Add approximately 6 litres of clean water to a clean bucket and then while stirring slowly add the 20kg bag of Coarse Mesh Coat. Coarse Mesh Coat should be mixed with with a heavy duty electric drill powering a high shear stirrer at approximately 600 r.p.m. The product should be mixed for a minimum of 2 minutes or long enough to provide a smooth lump-free blend. The consistency should be such that the material holds its shape when a finger is run through the surface. Let the mix stand for 5 minutes and give it a quick re-stir before application and adjust the final consistency.

The first coat or base coat of plaster is usually trowel applied with a long 20" x 4" or 20" x 5" steel trowel. Start at the corner of the wall and apply plaster to the full height of the substrate about one and a half meters wide (the width of the mesh). Apply at 3mm thickness. Place a layer of mesh (length longer than the wall) against the wet plaster at the top of the wall. Wipe the mesh very lightly at first into the plaster, starting from the middle and working out. Make sure there are no bubbles or wrinkles in the mesh. Once the mesh is flat against the plaster, apply pressure with the trowel and imbed the mesh just below the surface of the substrate. Repeat the process and ensure each adjacent drop of mesh overlaps its predecessor by at least 30mm.

For full system details refer to the Specialized installation guide.

Coarse Mesh Coat can also be used as a finish coat for Masonry and Brick substrates. It can be sprayed through a sagola gun to achieve a finely spiked texture finish.

SDS Number  
**DLX003952**

SDS Link  
[View SDS Link](#)

## 2nd Coat — Dulux Acratex Green Render Sealer

Coat Type  
**2nd Coat**

Datasheet  
**NZAC00038 Dulux Acratex Green Render Sealer**

Read the full Datasheet details at [Dulux Acratex Green Render Sealer](#)

### Application Methods



**Air Spray**



**Airless Spray**



**Brush**



**Roller**

	Min	Max	Recommended
Theoretical Spread Rate (m <sup>2</sup> /L)	<b>8</b>	<b>7</b>	<b>8</b>
Wet Film Per Coat (microns)	<b>126</b>	<b>143</b>	<b>126</b>
Dry Film Per Coat (microns)	<b>44</b>	<b>50</b>	<b>44</b>
Recoat Time **	<b>4 hours</b>	<b>4 hours</b>	<b>4 hours</b>

V.O.C. Level  
**20 g/L**

Meets ECNZ V.O.C. Requirements?

**Yes**

Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.

### Coating Application Details

**Brush, roller and airless spray**

Brush and roll at the same time to avoid picture framing.

Product should be thoroughly mixed before use. Refer to the Dulux Acratex Application Manual for detailed instructions. A 10-20mm nap roller is used depending on the type of surface profile being overcoated.

Typical Airless Spray set up is: Graco Ultra 500 using 0.017-0.019 spray tip at approx. 1000 psi.

SDS Number  
**DLX002555**

SDS Link  
[View SDS Link](#)

## 3rd Coat — Dulux Acratex 951 Coventry Coarse Sand Finish

Coat Type  
**3rd Coat**

Datasheet  
**NZAC00232 Dulux Acratex 951 Coventry Coarse Sand Finish**

Read the full Datasheet details at [Dulux Acratex 951 Coventry Coarse Sand Finish](#)

Application Methods



**Trowel**

**Tex Spray. Coventry Coarse should be tinted in accordance with AcraTex Tint Guide to the specified membrane top coat colour (Or a colour as close as possible to the specified colour in accordance with product /base tint rules)**

	Min	Max	Recommended
Theoretical Spread Rate (m²/L)	.8	.7	.8
Wet Film Per Coat (microns)	1333	1467	1333
Dry Film Per Coat (microns)	1000	1100	1000
Recoat Time **	24 hours	Indefinite	

V.O.C. Level  
**20 g/L untinted**

Meets ECNZ V.O.C. Requirements?  
**Not Applicable**

Coating Application Details

Product should be tinted & thoroughly mixed before use.

Refer to the DULUX AcraTex Application Manual for detailed application instructions.

Use masking to protect adjacent areas. The area should be patched and primed ready for final texture coat.

DULUX AcraTex 951 Coventry Coarse is applied by hawk and stainless steel trowel, then finished in a circular motion with the plastic finishing float to achieve an even granular appearance. Two applicators are required for most areas - one applying the other processing the finish. Delivery must be to a uniform thickness. Allow the material to stand for a short time before "rubbing up" with a float to produce the desired pattern/texture. Application must be in a brisk uniform fashion terminating when the whole area is complete, banded by a natural break such as an expansion joint, corner etc.

Application commenced on a single area must be completed uninterrupted.

Trowel and Hawk finished with a plastic float

SDS Number  
**DLXNZLEN002659**

SDS Link  
[View SDS Link](#)

**4th Coat — Dulux Acratex AcraShield Advance Matt**

Coat Type  
**4th Coat**

Datasheet  
**NZAC00074 Dulux Acratex AcraShield Advance Matt**

Read the full Datasheet details at [Dulux Acratex AcraShield Advance Matt](#)

Application Methods



**Air Spray**



**Airless Spray**



**Brush**



**Roller**

	Min	Max	Recommended
Theoretical Spread Rate (m²/L)	6	4.5	6
Wet Film Per Coat (microns)	167	222	167
Dry Film Per Coat (microns)	75	100	75
Recoat Time **	2 Hours	Indefinite	

V.O.C. Level  
**<90g/L**

Meets ECNZ V.O.C. Requirements?  
**Not Applicable**

Coating Application Details

**Brush, roller and airless spray**

Brush and roll at the same time to avoid picture framing.

Product should be thoroughly mixed before use. Refer to the Dulux Acratex Application Manual for detailed instructions. Dulux Acratex AcraShield Advance may be applied by brush, roller or airless spray. A 10-20mm nap roller is used depending on the type of texture being overcoated.

**Typical Airless Spray set up is:** Graco Ultra 500 using 0.019-0.021 spray tip at approx. 1000 psi.

SDS Number  
**DLX003010**

SDS Link  
[View SDS Link](#)

#### Coating System Notes

\* Practical Spreading Rate will vary from the quoted Theoretical Spreading Rate due to factors such as method and condition of application and surface roughness. \*\* Recoat times are quotes for 25°C and 50% relative humidity, these may vary under different conditions.

#### Disclaimer

This Specification is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Duspec+ document does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Duspec+ is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Duspec+ document, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Duspec+ document, and as recommended on the applicable Dulux Product Data Sheet and Safety Data Sheets for the relevant products (available from [www.duspecplus.co.nz](http://www.duspecplus.co.nz)). Climatic conditions at application time can affect Duspec+ documentation suitability and product performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Specification cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

**WHERE LEAD MAY BE PRESENT:** The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS/ NZS 4361 Parts 1 and 2 and Worksafe Australia or New Zealand guidelines.