

NZAC00831 Dulux Acratex 952 Spray On 2mm on New EIFS (Poly) [Exterior]

Scope of Works

DULUX AcraTex Spray-On 952 2mm texture is based on 100% pure acrylic binder and formulated for fast spray application to masonry surfaces.

Substrate and Substrate Preparation

Substrate Notes

EXTERIOR INSULATION AND FINISHING SYSTEM

EPS (expanded polystyrene), XPS (extruded polystyrene) and/or ICF (insulating concrete formwork) substrates are lightweight cladding materials. Polystyrene is a lightweight, durable polymer that is manufactured in a number of grades depending on the application. In building situations, the lightweight characteristic is a major advantage in providing structural design economies. These materials also provide excellent thermal insulation. They have been used throughout the world for over 40 years in an extremely wide range of applications.

An EIFS coating system generally consists of a base coat (including imbedded mesh), cementitious render and primer or primer and acrylic render, followed by a high build topcoat.

Substrate Preparation Notes

Only a Dulux approved applicator can install a Exsulite EIFS cladding system, following the Installation Manual.
Install other EIFS according to the manufactures instructions.

Coating System Summary

- 1st Coat Specialized Construction Products Coarse Mesh Coat
- 2nd Coat Dulux Acratex Green Render Sealer
- 3rd Coat Dulux Acratex 952 Spray On 2mm
- 4th Coat Dulux Acratex 968 Elastomeric 201 Matt

Coating System

1st Coat — Specialized Construction Products Coarse Mesh Coat

Coat Type
1st Coat

Datasheet
NZSP00023 Specialized Construction Products Coarse Mesh Coat

Read the full Datasheet details at [Specialized Construction Products Coarse Mesh Coat](#)

Application Methods



Trowel

	Min	Max	Recommended
Wet Film Per Coat (microns)	3000	4000	
Dry Film Per Coat (microns)	3000	4000	
Recoat Time **	8 Hours	Indefinite	

V.O.C. Level
<1 g/L

Meets ECNZ V.O.C. Requirements?
Not Applicable

Coating Application Details

MIXING: Add approximately 6 litres of clean water to a clean bucket and then while stirring slowly add the 20kg bag of Coarse Mesh Coat. Coarse Mesh Coat should be mixed with with a heavy duty electric drill powering a high shear stirrer at approximately 600 r.p.m. The product should be mixed for a minimum of 2 minutes or long enough to provide a smooth lump-free blend. The consistency should be such that the material holds its shape when a finger is run through the surface. Let the mix stand for 5 minutes and give it a quick re-stir before application and adjust the final consistency.

The first coat or base coat of plaster is usually trowel applied with a long 20" x 4" or 20" x 5" steel trowel. Start at the corner of the wall and apply plaster to the full height of the substrate about one and a half meters wide (the width of the mesh). Apply at 3mm thickness.

Place a layer of mesh (length longer than the wall) against the wet plaster at the top of the wall. Wipe the mesh very lightly at first into the plaster, starting from the middle and working out. Make sure there are no bubbles or wrinkles in the mesh. Once the mesh is flat against the plaster, apply pressure with the trowel and imbed the mesh just below the surface of the substrate. Repeat the process and ensure each adjacent drop of mesh overlaps its predecessor by at least 30mm.

For full system details refer to the Specialized installation guide.

Coarse Mesh Coat can also be used as a finish coat for Masonry and Brick substrates. It can be sprayed through a sagola gun to achieve a finely spiked texture finish.

SDS Number
DLX003952

SDS Link
[View SDS Link](#)

2nd Coat — Dulux Acratex Green Render Sealer

Coat Type
2nd Coat

Datasheet
NZAC00038 Dulux Acratex Green Render Sealer

Read the full Datasheet details at [Dulux Acratex Green Render Sealer](#)

Application Methods



Air Spray



Airless Spray



Brush



Roller

	Min	Max	Recommended
Theoretical Spread Rate (m ² /L)	8	7	8
Wet Film Per Coat (microns)	126	143	126
Dry Film Per Coat (microns)	44	50	44
Recoat Time **	4 hours	4 hours	4 hours

V.O.C. Level
20 g/L

Meets ECNZ V.O.C. Requirements?
Yes

Total Volatile Organic Content (TVOC) values are calculated in accordance to the stated methodology within Green Star Technical Manuals. The TVOC content is theoretically calculated as the sum total of the known VOC values of the product's raw material components. These materials include the base paint plus additional low VOC tinter required for non-factory packaged colours.

Coating Application Details

Brush, roller and airless spray

Brush and roll at the same time to avoid picture framing.

Product should be thoroughly mixed before use. Refer to the Dulux Acratex Application Manual for detailed instructions. A 10-20mm nap roller is used depending on the type of surface profile being overcoated.

Typical Airless Spray set up is: Graco Ultra 500 using 0.017-0.019 spray tip at approx. 1000 psi.

SDS Number
DLX002555

SDS Link
[View SDS Link](#)


3rd Coat — Dulux Acratex 952 Spray On 2mm




Coat Type
3rd Coat

Datasheet
NZAC00220 Dulux Acratex 952 Spray On 2mm

Read the full Datasheet details at [Dulux Acratex 952 Spray On 2mm](#)

Application Methods

<div> Hopper Gun</div>			
	Min	Max	Recommended
Theoretical Spread Rate (m²/L)	<div>1</div>	<div>.8</div>	<div>1</div>
Wet Film Per Coat (microns)	<div>1000</div>	<div>1308</div>	<div>1000</div>
Dry Film Per Coat (microns)	<div>650</div>	<div>850</div>	<div>650</div>
Recoat Time **	<div>24hours</div>	<div></div>	<div></div>
V.O.C. Level < 4 g/L untinted		Meets ECNZ V.O.C. Requirements? Not Applicable	
<div>Coating Application Details</div> <div>Hooper Gun with compressor</div> <div>Refer to the DULUX AcraTex Applicators Training Manual for detailed instructions. Apply in two passes using a DULUX AcraTex hopper gun. Thin slightly with water to aid application of the first pass to form a low profile motley base completely covering the substrate. Apply the second pass unthinned at 60% cover to achieve the required finish.</div> <div>Apply 2mm Grade at 0.8sq.m/l using a 6 to 8mm fluid nozzle set at 50-60 psi for the first pass and 30-40 psi for the second pass.</div>			
SDS Number 14557312		SDS Link View SDS Link	

4th Coat — Dulux Acratex 968 Elastomeric 201 Matt			
Coat Type 4th Coat		Datasheet NZAC00215 Dulux Acratex 968 Elastomeric 201 Matt	
Read the full Datasheet details at Dulux Acratex 968 Elastomeric 201 Matt			
Application Methods			
<div><div> Airless Spray</div><div> Brush</div><div> Roller</div></div>			
	Min	Max	Recommended
Theoretical Spread Rate (m²/L)	4	2	4
Wet Film Per Coat (microns)	250	500	250
Dry Film Per Coat (microns)	125	250	125
Recoat Time **	2 hours	Indefinite	
V.O.C. Level 60 g/L		Meets ECNZ V.O.C. Requirements? Not Applicable	
Coating Application Details Brush, Roller or Airless Spray Refer to the Dulux AcraTex Application Manual for detailed instructions. Stir contents thoroughly before and during use with a broad flat stirrer using an upward lifting action. When cutting in edges , brush and roll at the same time to avoid differences in gloss level. Application on single areas should be completed uninterrupted. All independent tests are available on request.			
SDS Number 6487		SDS Link View SDS Link	

Coating System Notes

* Practical Spreading Rate will vary from the quoted Theoretical Spreading Rate due to factors such as method and condition of application and surface roughness. ** Recoat times are quotes for 25°C and 50% relative humidity, these may vary under different conditions.

Disclaimer

This Specification is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Duspec+ document does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Duspec+ is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Duspec+ document, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Duspec+ document, and as recommended on the applicable Dulux Product Data Sheet and Safety Data Sheets for the relevant products (available from www.duspecplus.co.nz). Climatic conditions at application time can affect Duspec+ documentation suitability and product performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Specification cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS/ NZS 4361 Parts 1 and 2 and Worksafe Australia or New Zealand guidelines.