NZDU00572 Dulux Quantum Clearcoat Gloss on New Masonry [Exterior]

Scope of Works

Quantum Clear Coat is a premium quality, full gloss two-pack acrylic polyurethane. Quantum Clear Coat has been designed for superior weathering and gloss retention, while displaying the advantage of being recoatable with minimal surface preparation. Quantum Clear Coat, when fully cured, exhibits excellent graffiti resistance. This specification is designed as a anti graffiti system over bare substrates. ANTI GRAFFITI OVER BARE SUBSTRATE (EXCL TILT UP) - 2 PACK CLEAR GLOSS Gloss level: Gloss Coating type: Two pack solvent based acrylic clear polyurethane

Substrate and Substrate Preparation

Substrate Notes

This is a generic masonry and cementitious substrate. It includes concrete block substrates. The following substrates are excluded: Precast, Tilt-up and Off-form, Concrete Flooring, Roof Tiles and Cement Render. Other specialty masonry or cementitious substrates may also not be covered by this substrate.

BRICK
Bricks are predominantly kiln-fired clay, which can be glazed or unglazed. The glazing on glazed bricks should be ground or scabbled to improve adhesion of the coating system. Brickwork is often raked, so rendering requires much more material than face-laid brickwork. The surface must be clean and sound, free of dirt, grime, mould, fungus, stains, powdery mortar smears and all other contaminants. The surface should be examined to determine if it has been laid to specification (flush jointed or face laid) and that the surface variation is within acceptable tolerances. If applying a texture coating, the degree to which the texture coating camouflages flush walls depends on how flush the substrate has been constructed.

BLOCKWORK
Blockwork is largely cement based and highly porous, and usually flush-laid. The surface should be examined to determine if it has been laid to specification (flush jointed or face laid) and that the surface variation is within acceptable tolerances. The degree to which texture coatings camouflage flush walls depends on how flush the substrate has been constructed.

AUTOCLAVED AERATED CONCRETE (AAC)
AAC is manufactured from sand, lime and cement, to which is added water and aluminium paste. After mixing, the cement slurry is poured into moulds. The aluminium paste reacts with the alkaline elements in the mixture and forms hydrogen gas. This liberated gas expands the mixture forming extremely small finely dispersed air spaces. The product is removed from the mould after a few hours, cut to the required dimension and finally cured under pressure in a steam autoclave.
AAC Block Wall Systems are (typically) load-bearing external wall solutions for homes as an alternative to traditional double brick construction. Blocks are glued together (thin bed) using AAC Manufacturer's adhesive to a design standard of providing a level, fully filled joint.

AAC Panel is (typically) a 50 or 75mm panel of Autoclaved Aerated Concrete (AAC) with corrosion protected steel reinforcement embedded during production. This lightweight, yet solid masonry panel is designed for external cladding in timber or steel frame construction. Panels are glued together (thin bed) using AAC Manufacturer's adhesive to a design standard of providing a level, fully filled joint.

Substrate Preparation Notes

ASSESS SUITABILITY
Concrete, mortar and cement based products need to be fully cured for at least 28 days before painting, unless using Dulux AcraTex HAR primer.

PREPARE SURFACE
Remove any powdery layers, laitance, efflorescence and protrusions of mortar by detergent cleaning, wire brushing, water blasting or a suitable chemical treatment.

CLEAN
Clean the surface thoroughly by water blasting or detergent cleaning, where a commercial cleaner is added to hot or cold water and surface is washed / scrubbed thoroughly with a stiff bristle broom and then rinsed clean with fresh water. This may need to be repeated on extremely dirty surfaces to ensure removal of efflorescence or other poorly bonded surface material. Ensure that the surface is dry, clean and free from dust. Efflorescence may also be removed with an acid treatment, followed by washing down the surface with water.

REPAIR SURFACE IMPERFECTIONS
Fill any cracks or surface imperfections with a suitable filler or patching compound.

RENDERING OF NEW BRICK/ BLOCKWORK & MASONRY
Refer to Dulux AcraTex Texture coatings for suitable levelling and texture systems.

Coating System Summary

- 1st Coat — Dulux PREP WASH
- 2nd Coat — Dulux Quantum Clearcoat Gloss
- 3rd Coat — Dulux Quantum Clearcoat Gloss
- 4th Coat — Dulux Quantum Clearcoat Gloss

Coating System

1st Coat — Dulux PREP WASH

Coat Type	Datasheet
1st Coat	**NZDU00398 Dulux PREP WASH**

Read the full Datasheet details at Dulux PREP WASH

Application Methods

Brush

	Min	Max	Recommended
Theoretical Spread Rate (m²/L)	6	12	
Recoat Time **	n/a	n/a	n/a

Meets ECNZ V.O.C. Requirements?
Not Applicable

Coating Application Details

Apply by broom or brush. Or by garden sprayer.
1. Add one part Dulux Prep Wash concentrate to one part water in a clean plastic bucket and mix well.
2. Test on a small inconspicuous area at recommended dilution to determine effectiveness and strength required.
3. Apply diluted Dulux Prep Wash solution to walls/roof/trim with a broom/brush or garden sprayer. Leave the solution on the surface until mould and mildew stains disappear or soften (approximately 10 minutes), avoiding allowing the solution to dry out. Scrub vigorously.
4. Rinse off the surface with water using a high pressure or garden hose and allow surface to dry. Surface may be slippery while wet (roof). Stubborn stains may require longer time, more vigorous scrubbing, or additional treatment. Severely stained surfaces may need a power washer, or treatment with undiluted Dulux Prep Wash concentrate.

SDS Number	SDS Link
000000022880	**View SDS Link**

2nd Coat — Dulux Quantum Clearcoat Gloss

Coat Type	Datasheet
2nd Coat	**NZDU00525 Dulux Quantum Clearcoat Gloss**

Read the full Datasheet details at Dulux Quantum Clearcoat Gloss

Application Methods

Airless Spray

	Min	Max	Recommended
Theoretical Spread Rate (m²/L)			9.5
Wet Film Per Coat (microns)			100
Dry Film Per Coat (microns)			45

Recoat Time **	7 Hours	Indefinite	

Meets ECNZ V.O.C. Requirements?
Not Applicable

3rd Coat — Dulux Quantum Clearcoat Gloss

Coat Type	Datasheet
3rd Coat	**NZDU00525 Dulux Quantum Clearcoat Gloss**

Read the full Datasheet details at Dulux Quantum Clearcoat Gloss

Application Methods

Airless Spray

	Min	Max	Recommended
Theoretical Spread Rate (m²/L)			9.5
Wet Film Per Coat (microns)			100
Dry Film Per Coat (microns)			45
Recoat Time **	7 Hours	Indefinite	

Meets ECNZ V.O.C. Requirements?
Not Applicable

4th Coat — Dulux Quantum Clearcoat Gloss

Coat Type	Datasheet
4th Coat	**NZDU00525 Dulux Quantum Clearcoat Gloss**

Read the full Datasheet details at Dulux Quantum Clearcoat Gloss

Application Methods

Airless Spray

	Min	Max	Recommended
Theoretical Spread Rate (m²/L)			9.5
Wet Film Per Coat (microns)			100
Dry Film Per Coat (microns)			45
Recoat Time **	7 Hours	Indefinite	

Meets ECNZ V.O.C. Requirements?
Not Applicable

Coating System Notes
* Theorectical Coverage is the area is the area covered by 1 Litre of material at the specifiaction 'Dry Film Thickness' without a loss to a smooth and non porous surface.

Disclaimer

This Specification is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Duspec+ document does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Duspec+ is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Duspec+ document, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Duspec+ document, and as recommended on the applicable Dulux Product Data Sheet and Safety Data Sheets for the relevant products (available from www.duspecplus.co.nz). Climatic conditions at application time can affect Duspec+ documentation suitability and product performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Specification cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS/ NZS 4361 Parts 1 and 2 and Worksafe Australia or New Zealand guidelines.