

NZDU01641 Dulux Enviropoxy WBE Semi Gloss on New Masonry [Interior]

Scope of Works

DULUX Enviropoxy WBE is a high performance water based acrylic epoxy topcoat that has been developed especially for Australasian conditions. It displays superior gloss retention and resistance to chalking and yellowing compared to traditional solvent based epoxies. INTERIOR MASONRY WALLS - HIGH DEMAND PAINT Gloss level: Semi Gloss Coating type: Epoxy primer/Waterborne acrylic epoxy

Substrate and Substrate Preparation

Substrate Notes

This is a generic masonry and cementitious substrate. It includes concrete block substrates. The following substrates are excluded: Precast, Tilt-up and Off-form, Concrete Flooring, Roof Tiles and Cement Render. Other specialty masonry or cementitious substrates may also not be covered by this substrate.

BRICK

Bricks are predominantly kiln-fired clay, which can be glazed or unglazed. The glazing on glazed bricks should be ground or scabbled to improve adhesion of the coating system. Brickwork is often raked, so rendering requires much more material than face-laid brickwork. The surface must be clean and sound, free of dirt, grime, mould, fungus, stains, powdery mortar smears and all other contaminants. The surface should be examined to determine if it has been laid to specification (flush jointed or face laid) and that the surface variation is within acceptable tolerances. If applying a texture coating, the degree to which the texture coating camouflages flush walls depends on how flush the substrate has been constructed.

BLOCKWORK

Blockwork is largely cement based and highly porous, and usually flush-laid. The surface should be examined to determine if it has been laid to specification (flush jointed or face laid) and that the surface variation is within acceptable tolerances. The degree to which texture coatings camouflage flush walls depends on how flush the substrate has been constructed.

AUTOCLAVED AERATED CONCRETE (AAC)

AAC is manufactured from sand, lime and cement, to which is added water and aluminium paste. After mixing, the cement slurry is poured into moulds. The aluminium paste reacts with the alkaline elements in the mixture and forms hydrogen gas. This liberated gas expands the mixture forming extremely small finely dispersed air spaces. The product is removed from the mould after a few hours, cut to the required dimension and finally cured under pressure in a steam autoclave.

AAC Block Wall Systems are (typically) load-bearing external wall solutions for homes as an alternative to traditional double brick construction. Blocks are glued together (thin bed) using AAC Manufacturer's adhesive to a design standard of providing a level, fully filled joint.

AAC Panel is (typically) a 50 or 75mm panel of Autoclaved Aerated Concrete (AAC) with corrosion protected steel reinforcement embedded during production. This lightweight, yet solid masonry panel is designed for external cladding in timber or steel frame construction. Panels are glued together (thin bed) using AAC Manufacturer's adhesive to a design standard of providing a level, fully filled joint.

Substrate Preparation Notes

ASSESS SUITABILITY

Concrete, mortar and cement based products need to be fully cured for at least 28 days before painting, unless using Dulux AcraTex HAR primer.

PREPARE SURFACE

Remove any powdery layers, laitance, efflorescence and protrusions of mortar by detergent cleaning, wire brushing, water blasting or a suitable chemical treatment.

CLEAN

Clean the surface thoroughly by water blasting or detergent cleaning, where a commercial cleaner is added to hot or cold water and surface is washed / scrubbed thoroughly with a stiff bristle broom and then rinsed clean with fresh water. This may need to be repeated on extremely dirty surfaces to ensure removal of efflorescence or other poorly bonded surface material. Ensure that the surface is dry, clean and free from dust. Efflorescence may also be removed with an acid treatment, followed by washing down the surface with water.

REPAIR SURFACE IMPERFECTIONS

Fill any cracks or surface imperfections with a suitable filler or patching compound.

RENDERING OF NEW BRICK/ BLOCKWORK & MASONRY

Refer to Dulux AcraTex Texture coatings for suitable levelling and texture systems.

Coating System Summary

- 1st Coat Dulux Luxepoxy 4 White Primer
- 2nd Coat Dulux Enviropoxy WBE Semi Gloss
- 3rd Coat Dulux Enviropoxy WBE Semi Gloss

Coating System

1st Coat — Dulux Luxepoxy 4 White Primer

Coat Type
1st Coat

Datasheet
NZDU00466 Dulux Luxepoxy 4 White Primer

Read the full Datasheet details at [Dulux Luxepoxy 4 White Primer](#)

Application Methods

 Air Spray
  Airless Spray
  Brush
  Roller

	Min	Max	Recommended
Theoretical Spread Rate (m ² /L)	<input type="text"/>	<input type="text"/>	8.6
Wet Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	125
Dry Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	50
Recoat Time **	8 Hours	Indefinite	<input type="text"/>

Meets ECNZ V.O.C. Requirements?
Not Applicable

2nd Coat — Dulux Enviropoxy WBE Semi Gloss

Coat Type
2nd Coat

Datasheet
NZDU00489 Dulux Enviropoxy WBE Semi Gloss

Read the full Datasheet details at [Dulux Enviropoxy WBE Semi Gloss](#)

Application Methods

 Air Spray
  Airless Spray
  Brush
  Roller

	Min	Max	Recommended
Theoretical Spread Rate (m ² /L)	<input type="text"/>	<input type="text"/>	7.6
Wet Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	130
Dry Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	50
Recoat Time **	4 Hours	4 Weeks	<input type="text"/>

Meets ECNZ V.O.C. Requirements?
Not Applicable

3rd Coat — Dulux Enviropoxy WBE Semi Gloss

Coat Type 3rd Coat		Datasheet NZDU00489 Dulux Enviropoxy WBE Semi Gloss	
Read the full Datasheet details at Dulux Enviropoxy WBE Semi Gloss			
Application Methods			
<div>  Air Spray  Airless Spray  Brush  Roller </div>			
	Min	Max	Recommended
Theoretical Spread Rate (m ² /L)	<input type="text"/>	<input type="text"/>	7.6
Wet Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	130
Dry Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	50
Recoat Time **	4 Hours	4 Weeks	<input type="text"/>
Meets ECNZ V.O.C. Requirements? Not Applicable			
Coating System Notes * Theoretical Coverage is the area is the area covered by 1 Litre of material at the specifiaction 'Dry Film Thickness' without a loss to a smooth and non porous surface.			

Disclaimer

This Specification is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Duspec+ document does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Duspec+ is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Duspec+ document, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Duspec+ document, and as recommended on the applicable Dulux Product Data Sheet and Safety Data Sheets for the relevant products (available from www.duspecplus.co.nz). Climatic conditions at application time can affect Duspec+ documentation suitability and product performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Specification cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS/ NZS 4361 Parts 1 and 2 and Worksafe Australia or New Zealand guidelines.