

NZMA00058 Maxiproof Maxiproof Gloss on Painted Concrete Flooring [Interior]

Description

Maxiproof Gloss is an aliphatic interior/ exterior moisture-cured polyurethane with added UV absorbers. It is designed to produce a hardwearing, traffic tough finish that is UV, heat, scuff and scratch resistant. Maxiproof Gloss is ideal for extreme, high-traffic commercial areas such as shopping malls, sports floors, boards, bars and cafes. Maxiproof Gloss also provides a tough, clear finish for bench tops, furniture and joinery, especially if exposed to direct sunlight.

Substrate and Substrate Preparation

Substrate Notes

CONCRETE

A mixture of Portland cement, fine and coarse mineral aggregates, water and additives. Concrete is generally reinforced with mild steel bars and/or mesh. Unless the concrete is suitably coated, it is prone to spalling, particularly in or near cities, industrial areas and near the coast. Concrete comes in a range of densities, and these can affect the adhesion of coatings.

Substrate Preparation Notes

ASSESS SUITABILITY

Inspect to determine the degree of deterioration of existing coatings. Identification of the existing coating is also very helpful in determining the repaint system. Check coating adhesion using the cross-cut adhesion test, carried out in various locations.

REMOVE SURFACE CONTAMINANTS

Clean to remove all dirt, dust, efflorescence, laitance, powdery surfaces, mould and all other surface contaminants by using a suitable cleaning agent, such as Dulux Prep Wash and rinsing/water blasting clean with water. Water blasting will also give a good indication as to the coatings integrity. Efflorescence may also be removed with an acid treatment, followed by washing down the surface with water.

REPAIR SURFACE IMPERFECTIONS

Prepare all areas that have poor adhesion, cracking, peeling and flaking by sanding, power sanding, scraping, wire brushing, grit blasting, burning off or chemical stripping as appropriate, to leave a clean surface. Feather edges of the surrounding sound paint to completely remove visual ridges and wash / dust off to remove debris. Any major design faults leading to structural failure must be corrected prior to repainting. Use an acrylic based patching compound with the addition of 10-20% fresh Portland cement to patch any surface defects.

SANDING

Sand the entire cleaned coating to an even flat gloss level to provide a smooth, even surface and to provide a good key for the new coating system to adhere to. Ensure all sanding dust is removed prior to continuing.

ADDITIONAL NOTES:

- Ensure all previously painted enamel finishes are thoroughly abraded to ensure adequate adhesion of subsequent coating system.
- For successful floor coatings, adequate key into the substrate is vital. If the previous coating does not have adequate key into the substrate the coating may need to be removed and the substrate properly prepared.

Coating System Summary

- | | |
|---------------|---------------------------|
| • Spot Primer | Maxiproof Maxiproof Gloss |
| • 1st Coat | Maxiproof Maxiproof Gloss |
| • 2nd Coat | Maxiproof Maxiproof Gloss |

Coating System

Spot Primer — Maxiproof Maxiproof Gloss

Coat Type Spot Primer	Datasheet NZMA00007 Maxiproof Maxiproof Gloss
---------------------------------	---

Read the full Datasheet details at [Maxiproof Maxiproof Gloss](#)

Application Methods



	Min	Max	Recommended
Theoretical Spread Rate (m ² /L)	12.1	8	8
Wet Film Per Coat (microns)	83	125	125
Dry Film Per Coat (microns)	32	48	48
Recoat Time **	8 Hours	Indefinite	

V.O.C. Level 562 g/L	Meets ECNZ V.O.C. Requirements? Not Applicable
--------------------------------	--

Coating Application Details

Applicator pad, brush or short-nap mohair roller.
Product may be applied by applicator pad, brush or short-nap mohair roller, however ensure care is taken to minimise air bubbles. Always lay off along the grain. Always work out of direct sunlight. Timber being coated should be dry and cool to the touch. Follow all other good coating practices.
IMPORTANT Minimise the exposure of Maxiproof Gloss to moisture in the air by ensuring that the container is sealed immediately after decanting a sufficient amount for immediate use. DO NOT return unused product to the original container.
For new builds, exposed timber should be coated on all faces, edges, and ends before being attached to the building framework. For timber end grain it is recommended to seal following the full product specification - 3 coats.
Stir thoroughly before and during use with a broad, flat stirrer to maintain a uniform solution.
Allow approximately 8 hours for 1st coat to dry. Lightly sand 1st coat. Apply 2nd and 3rd coats unthinned. Lightly sand between coats.
Maxiproof Gloss can be sprayed but application must be in accordance with spray-painting regulations. Forced air respirators are compulsory.

SDS Number 22836	SDS Link View SDS Link
----------------------------	---

1st Coat — Maxiproof Maxiproof Gloss

Coat Type 1st Coat	Datasheet NZMA00007 Maxiproof Maxiproof Gloss
------------------------------	---

Read the full Datasheet details at [Maxiproof Maxiproof Gloss](#)




Application Methods



	Min	Max	Recommended
Theoretical Spread Rate (m ² /L)	12.1	8	8
Wet Film Per Coat (microns)	83	125	125
Dry Film Per Coat (microns)	32	48	48

Recoat Time **	8 Hours	Indefinite	
V.O.C. Level 562 g/L	Meets ECNZ V.O.C. Requirements? Not Applicable		
<p>Coating Application Details</p> <p>Applicator pad, brush or short-nap mohair roller.</p> <p>Product may be applied by applicator pad, brush or short-nap mohair roller, however ensure care is taken to minimise air bubbles. Always lay off along the grain. Always work out of direct sunlight. Timber being coated should be dry and cool to the touch. Follow all other good coating practices.</p> <p>IMPORTANT Minimise the exposure of Maxiproof Gloss to moisture in the air by ensuring that the container is sealed immediately after decanting a sufficient amount for immediate use. DO NOT return unused product to the original container.</p> <p>For new builds, exposed timber should be coated on all faces, edges, and ends before being attached to the building framework. For timber end grain it is recommended to seal following the full product specification - 3 coats.</p> <p>Stir thoroughly before and during use with a broad, flat stirrer to maintain a uniform solution.</p> <p>Allow approximately 8 hours for 1st coat to dry. Lightly sand 1st coat. Apply 2nd and 3rd coats unthinned. Lightly sand between coats.</p> <p>Maxiproof Gloss can be sprayed but application must be in accordance with spray-painting regulations. Forced air respirators are compulsory.</p>			
SDS Number 22836	SDS Link View SDS Link		

2nd Coat — Maxiproof Maxiproof Gloss

Coat Type 2nd Coat		Datasheet NZMA00007 Maxiproof Maxiproof Gloss	
Read the full Datasheet details at Maxiproof Maxiproof Gloss			
Application Methods			
<div><div> Brush</div><div> Roller</div><div> Pad</div></div>			
	Min	Max	Recommended
Theoretical Spread Rate (m²/L)	12.1	8	8
Wet Film Per Coat (microns)	83	125	125
Dry Film Per Coat (microns)	32	48	48
Recoat Time **	8 Hours	Indefinite	
V.O.C. Level 562 g/L		Meets ECNZ V.O.C. Requirements? Not Applicable	
Coating Application Details			
<p>Applicator pad, brush or short-nap mohair roller.</p> <p>Product may be applied by applicator pad, brush or short-nap mohair roller, however ensure care is taken to minimise air bubbles. Always lay off along the grain. Always work out of direct sunlight. Timber being coated should be dry and cool to the touch. Follow all other good coating practices.</p> <p>IMPORTANT Minimise the exposure of Maxiproof Gloss to moisture in the air by ensuring that the container is sealed immediately after decanting a sufficient amount for immediate use. DO NOT return unused product to the original container.</p> <p>For new builds, exposed timber should be coated on all faces, edges, and ends before being attached to the building framework. For timber end grain it is recommended to seal following the full product specification - 3 coats.</p> <p>Stir thoroughly before and during use with a broad, flat stirrer to maintain a uniform solution.</p> <p>Allow approximately 8 hours for 1st coat to dry. Lightly sand 1st coat. Apply 2nd and 3rd coats unthinned. Lightly sand between coats.</p> <p>Maxiproof Gloss can be sprayed but application must be in accordance with spray-painting regulations. Forced air respirators are compulsory.</p>			
SDS Number 22836		SDS Link View SDS Link	

Coating System Notes

* Practical Spreading Rate will vary from the quoted Theoretical Spreading Rate due to factors such as method and condition of application and surface roughness. ** Recoat times are quotes for 25°C and 50% relative humidity, these may vary under different conditions.

Disclaimer

This Specification is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Duspec+ document does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Duspec+ is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Duspec+ document, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Duspec+ document, and as recommended on the applicable Dulux Product Data Sheet and Safety Data Sheets for the relevant products (available from www.duspecplus.co.nz). Climatic conditions at application time can affect Duspec+ documentation suitability and product performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Specification cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS/ NZS 4361 Parts 1 and 2 and Worksafe Australia or New Zealand guidelines.