

## NZDU00793 Dulux Luxathane R Gloss on Painted Non-Ferrous Metals [Interior]

### Scope of Works

DULUX LUXATHANE® R is a full gloss, two component acrylic polyurethane which displays the advantage of being recoatable with minimum surface preparation.

### Substrate and Substrate Preparation

#### Substrate Notes

This is a generic non-ferrous metal substrate. Please see the respective substrate for: steel, galvanised steel, precoated sheet steel. Other specialty metal substrates may also not be covered by this substrate.

#### ALUMINIUM & ALLOYS

Aluminium and its alloys rapidly oxidise on exposure, forming a chemically inert, protective layer that protects the metal from further corrosion.

Aluminium and its alloys may be extremely smooth or contaminated with greases, oils and foreign matter leading to poor paint adhesion and reduced lifetime. Careful cleaning and thorough abrasion of the surface must be carried out prior to painting to ensure maximum coating performance.

#### ANODISED ALUMINIUM

Anodising is an electro-chemical process which physically alters the surface of the metal to produce a very smooth, tough, dense, invisible oxide layer on the surface. The aluminium surface is 'passivated' and sealed and therefore unable to bond with any organic coating, including powder coatings unless proper surface preparation is carried out to ensure adequate adhesion of the applied finish.

#### COPPER

Copper metal has a dull brown metallic lustre but will oxidise to the familiar chalky green patina often seen on copper domes on heritage buildings. This green patina must be completely removed prior to painting.

#### BRASS

Brass is an alloy (blend) of copper and zinc. Brass can be polished to a bright, shiny, lustrous metallic dark gold appearance but is prone to tarnishing (surface corrosion), particularly on contact with skin, and therefore should not be handled with bare hands. Brass is very smooth and may be coated with oils leading to poor paint adhesion and reduced lifetime. Careful cleaning and thorough abrasion of the surface must be carried out prior to painting to ensure maximum coating performance.

#### BRONZE

Bronze is an alloy (blend) of copper and tin and has a shiny, lustrous brown metallic appearance that is prone to tarnishing (surface corrosion) to a dusty green patina with time. Bronze is generally quite smooth and may be contaminated with oils leading to poor paint adhesion and reduced lifetime. Careful cleaning and thorough abrasion of the surface must be carried out prior to painting to ensure maximum coating performance.

#### Substrate Preparation Notes

##### ASSESS SUITABILITY

Inspect to determine the degree of deterioration of existing coatings. Identification of the existing coating is also very helpful in determining the repaint system. Check coating adhesion using the cross-cut adhesion test, carried out in various locations.

##### CLEAN SURFACE

Degrease surface with an alkaline detergent, such as Dulux Prep Wash, and rinse with fresh potable water until free of residue. Repeat until the surface is clean. Alternatively, the surface can be cleaned by water blasting.

##### ABRADE SURFACE

Abrade surface to remove gloss and chalkiness, to achieve a smooth, even, sound surface and to provide a good key for the new coating system. Ensure all dust is removed. Complete removal of heavy chalky buildup may require wire brush or power tool cleaning back to sound paint layers before sanding. Feather edges of the surround sound paint. Ensure all dust is removed prior to continuing.

##### PRIME

Apply a suitable primer to any bare metal areas as soon as possible, to reduce the risk of corrosion.

##### ADDITIONAL NOTES

- The existing coating must be sound and firmly adherent to the substrate. Cross-hatch adhesion testing must be carried out prior to applying this coating system.
- The existing painted surface can be solvent sensitive. The nominated primer should therefore be applied to a "test area" prior to work commencing to ensure that the new coatings will not adversely affect the old coatings. If 'frying' or 'wrinkling' occurs then an alternative system will need to be employed.

##### INDUSTRIAL

##### ASSESS SUITABILITY

Inspect to determine the degree of deterioration of existing coatings. Identification of the existing coating is also very helpful in determining the repaint system. Check coating adhesion using the cross-cut adhesion test, carried out in various locations. Refer to relevant sections of AS 1580.408.4

#### CLEAN SURFACE

Degrease surface with an alkaline detergent, such as Dulux Prep Wash, and rinse with fresh potable water until free of residue. Repeat until the surface is clean. Refer to relevant sections of AS1627.1.

#### ABRADE SURFACE

Abrade surface to remove gloss and chalkiness, to achieve a smooth, even, sound surface and to provide a good key for the new coating system. Ensure all dust is removed. Complete removal of coatings that failed the adhesion test may require wire brush or power tool cleaning back to sound paint layers before sanding. Feather edges of the surround sound paint. Ensure all dust is removed prior to continuing. Refer to relevant sections of AS1627.2.

#### PRIME

Apply a suitable primer to any bare metal areas as soon as possible, to reduce the risk of corrosion.

#### Coating System Summary

- Spot Primer Dulux Luxepoxy 4 White Primer
- 1st Coat Dulux Luxathane R Gloss

#### Coating System

##### Spot Primer — Dulux Luxepoxy 4 White Primer

Coat Type <b>Spot Primer</b>	Datasheet <b>NZDU00466 Dulux Luxepoxy 4 White Primer</b>
---------------------------------	---

Read the full Datasheet details at [Dulux Luxepoxy 4 White Primer](#)

#### Application Methods

 Air Spray
  Airless Spray
  Brush
  Roller

	Min	Max	Recommended
Theoretical Spread Rate (m <sup>2</sup> /L)	<input type="text"/>	<input type="text"/>	<b>8.6</b>
Wet Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	<b>125</b>
Dry Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	<b>50</b>
Recoat Time **	<b>8 Hours</b>	<b>Indefinite</b>	<input type="text"/>

Meets ECNZ V.O.C. Requirements?

**Not Applicable**

##### 1st Coat — Dulux Luxathane R Gloss

Coat Type <b>1st Coat</b>	Datasheet <b>NZDU00491 Dulux Luxathane R Gloss</b>
------------------------------	---

Read the full Datasheet details at [Dulux Luxathane R Gloss](#)

#### Application Methods

 Air Spray
  Airless Spray
  Brush
  Roller

	Min	Max	Recommended
Theoretical Spread Rate (m <sup>2</sup> /L)	<input type="text"/>	<input type="text"/>	<b>9.2</b>

Wet Film Per Coat (microns)			110
Dry Film Per Coat (microns)			50
Recoat Time **	16 Hours	Indefinite	
Meets ECNZ V.O.C. Requirements? <b>Not Applicable</b>			

**Coating System Notes**

\* Theoretical Coverage is the area is the area covered by 1 Litre of material at the specifiaction 'Dry Film Thickness' without a loss to a smooth and non porous surface.

**Disclaimer**

This Specification is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Duspec+ document does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Duspec+ is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Duspec+ document, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Duspec+ document, and as recommended on the applicable Dulux Product Data Sheet and Safety Data Sheets for the relevant products (available from [www.duspecplus.co.nz](http://www.duspecplus.co.nz)). Climatic conditions at application time can affect Duspec+ documentation suitability and product performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Specification cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

**WHERE LEAD MAY BE PRESENT:** The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS/ NZS 4361 Parts 1 and 2 and Worksafe Australia or New Zealand guidelines.