

NZDU00650 Dulux Quantum FX Gloss on New Steel [Exterior]

Scope of Works

QUANTUM is a premium quality, full gloss two-pack metallic polyurethane. EXTERIOR STEEL - PUR4 - LONG TERM SYSTEM - METALLIC FINISH
Gloss level: Gloss Coating type: Epoxy zinc rich primer/Intermediate/Polyurethane gloss (metallic finish) Preparation: Abrasive blast to AS 1627.4 Class 2.5

Substrate and Substrate Preparation

Substrate Notes

This is a generic steel or iron substrate. Please see the respective substrate for: non-ferrous metals, galvanised steel, precoated sheet steel. Other specialty metal substrates may also not be covered by this substrate.

Uncoated ferrous metal is very unstable and will readily react with water and oxygen to form oxides (rust). The presence of salts will speed up rust formation.

Millscale is a shiny, bluish iron oxide produced by heat and pressure during manufacture and is often mistaken for shop primer or clean steel. Millscale is very difficult to remove by hand and should be abrasive blast cleaned off. The presence of millscale is responsible for a significant proportion of coating failures.

MILD STEEL

Mild steel contains less than 0.25% carbon. New mild steel surfaces should be inspected for millscale, rust, sharp edges, burr marks and welding flux, forming or machine oils, salts, chemical contamination or mortar splashes on them, all of which must be removed.

CAST IRON

Cast iron is a carbon-steel alloy containing substantial amounts of graphite (usually above 2.5%) which has been cast and therefore does not contain welds.

BLACK STEEL

Ferrous metal partially protected by a thin outer layer of black iron oxide (Magnetite). Rust protection offered with black steel is minimal and is often treated with an oil coating during manufacture to inhibit the rust process.

WROUGHT IRON

A historic grade of iron, with a low carbon content (0.1-0.25%) but significant levels of impurities. It has little use today and has been replaced by mild steel.

Substrate Preparation Notes

DOMESTIC

CLEAN

Remove all surface contamination such as oil, grease or dirt by washing with an alkaline detergent, such as Dulux Prep Wash, and rinse with fresh potable water.

PREPARE SURFACE

Surface shall be power tool cleaned, to remove all rust, weld flux and mill scale, back to clean, corrosion-free metal, and to provide a suitable key for the coating system. Remove all residual loose matter resulting from the cleaning process by brush, vacuum, or clean, compressed air.

PRIME

Apply a suitable, corrosion-inhibiting primer to any bare metal areas as soon as possible, before the surface oxidises or becomes contaminated.

RUST AFFECTED STEEL

1. Remove any loose or flaking coating back to a hard edge by scraper or power tool. Feather back all edges to remove ridges. Abrade surface of remaining coating to provide a suitable surface key for adhesion of the new coating system.
2. Using wire brush or power tool cleaning methods as appropriate, clean all bare metal surfaces and rust-affected areas. Remove filings, preferably by vacuum or compressed air. Ensure that the surface is clean, corrosion-free and dry immediately prior to application of primer coat.
3. Spot prime all bare metal with an appropriate, corrosion-inhibiting primer as soon as possible, before the surface oxidises or becomes contaminated.

INDUSTRIAL

CLEAN

Wash, degrease and remove all surface contaminants in accordance with AS1627.1 with a free-rinsing, alkaline detergent, such as Dulux Prep Wash. Wash with fresh potable water and ensure that all soluble salts are removed in accordance with AS 3894.6 methods A&D.

PREPARE SURFACE

Grind all sharp edges with a power tool to a minimum radius of 2 mm. Power tool clean welds to AS1627.2 Class 2 to remove roughness. Remove filings, preferably by vacuum or compressed air. Abrasive blast clean all steel surfaces to be painted in accordance with AS1627.4 to visual standard AS1627.9 Class 2.5 (equivalent to ISO8501-1, Sa 2.5: Very Thorough Blast-Cleaning). Use a non-metallic medium that will generate a surface profile of 35 to 65 microns (as tested to AS3894.5 Method A.)

PRIME

Commence application within 4 hours of abrasive blast cleaning or before surface becomes contaminated, otherwise repeat abrasive blasting step. Stripe coat welds, bolts, boltholes and all edges with primer before application of full primer coat nominated in the Coating System section of the specification.

TREATMENT OF ON SITE WELDING

1. Remove weld spatter.
2. Power tool clean welds to AS1627.2 Class 2 to remove roughness. Remove filings, preferably by vacuum or compressed air.
3. Prime welds immediately with the nominated primer before contamination can reoccur. Ensure that the primer overlaps the sound adjacent coating by not less than 25mm or greater than 50mm.
4. Apply intermediate and topcoats over the primed welds to match the surrounding coating system, overlapping the sound adjacent coating by not less than 25mm or greater than 50mm.

Coating System Summary

- 1st Coat Dulux Zincanode 402 Matt
- 2nd Coat Dulux Duremax GPE Semi Gloss
- 3rd Coat Dulux Quantum FX Gloss
- 4th Coat Dulux Quantum Clearcoat Gloss

Coating System

1st Coat — Dulux Zincanode 402 Matt

Coat Type 1st Coat	Datasheet NZDU00463 Dulux Zincanode 402 Matt
------------------------------	--

Read the full Datasheet details at [Dulux Zincanode 402 Matt](#)

Application Methods

-  Air Spray
  Airless Spray
  Brush
  Roller

	Min	Max	Recommended
Theoretical Spread Rate (m ² /L)	8	6	6.4
Wet Film Per Coat (microns)	125	165	155
Dry Film Per Coat (microns)	60	80	75
Recoat Time **	5 Hours	Indefinite	

Meets ECNZ V.O.C. Requirements?
Not Applicable

2nd Coat — Dulux Duremax GPE Semi Gloss

Coat Type 2nd Coat	Datasheet NZDU00488 Dulux Duremax GPE Semi Gloss
------------------------------	--

Read the full Datasheet details at [Dulux Duremax GPE Semi Gloss](#)


Application Methods

-  Air Spray
  Airless Spray
  Brush
  Roller


	Min	Max	Recommended
Theoretical Spread Rate (m ² /L)			5.8

Wet Film Per Coat (microns)			175
Dry Film Per Coat (microns)			125
Recoat Time **	8 Hours	4 Weeks*	
Meets ECNZ V.O.C. Requirements? Not Applicable			

3rd Coat — Dulux Quantum FX Gloss

Coat Type 3rd Coat		Datasheet NZDU00524 Dulux Quantum FX Gloss	
Read the full Datasheet details at Dulux Quantum FX Gloss			
Application Methods			
<div><div></div><div>Airless Spray</div></div>			
	Min	Max	Recommended
Theoretical Spread Rate (m²/L)	<div></div>	<div></div>	<div>8.2</div>
Wet Film Per Coat (microns)	<div></div>	<div></div>	<div>120</div>
Dry Film Per Coat (microns)	<div></div>	<div></div>	<div>55</div>
Recoat Time **	<div>7 Hours</div>	<div>Indefinite</div>	<div></div>
Meets ECNZ V.O.C. Requirements? Not Applicable			

4th Coat — Dulux Quantum Clearcoat Gloss

Coat Type 4th Coat		Datasheet NZDU00525 Dulux Quantum Clearcoat Gloss	
Read the full Datasheet details at Dulux Quantum Clearcoat Gloss			
Application Methods			
<div> Airless Spray</div>			
	Min	Max	Recommended
Theoretical Spread Rate (m²/L)	<div></div>	<div></div>	<div>9.5</div>
Wet Film Per Coat (microns)	<div></div>	<div></div>	<div>100</div>
Dry Film Per Coat (microns)	<div></div>	<div></div>	<div>45</div>
Recoat Time **	<div>7 Hours</div>	<div>Indefinite</div>	<div></div>
Meets ECNZ V.O.C. Requirements? Not Applicable			

Coating System Notes

* Theoretical Coverage is the area is the area covered by 1 Litre of material at the specification 'Dry Film Thickness' without a loss to a smooth and non porous surface.

Disclaimer

This Specification is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Duspec+ document does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Duspec+ is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Duspec+ document, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Duspec+ document, and as recommended on the applicable Dulux Product Data Sheet and Safety Data Sheets for the relevant products (available from www.duspecplus.co.nz). Climatic conditions at application time can affect Duspec+ documentation suitability and product performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Specification cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS/ NZS 4361 Parts 1 and 2 and Worksafe Australia or New Zealand guidelines.