

NZDU00589 Dulux Ceiling White +Plus Kitchen & Bathroom on New Paperfaced Plasterboard [Interior]

Scope of Works

DULUX Ceiling White +PLUS Kitchen & Bathroom is an advanced whole-of-home ceiling formulation with Mouldshield® protection. It is tintable to light colours and has superior opacity to provide excellent hiding power, making it perfect for the whole home.

Substrate and Substrate Preparation

Substrate Notes

White plaster is the main ingredient in paperfaced plasterboard and other similar materials. They are generally used for interior ceilings and walls.

PAPERFACED PLASTERBOARD (eg GIB® Board)

Paperfaced plasterboard is set plaster sandwiched between cardboard faces. The edges are recessed to allow the joints to be flushed with cornice cement or plaster compound. Paperfaced plasterboard should be flat and smooth on jointed areas, free of dust and have undamaged paper surfaces.

Ensure paper has not been scuffed by sanding at jointed areas. Poor flushing of the joints or inadequate priming will cause visual "banding" when painted. Ensure a high quality of levelling and sufficient priming to unify surface porosity.

Note: This specification is for plasterboard, not fibrous or set plaster.

Substrate Preparation Notes

REPAIR SURFACE IMPERFECTIONS

Fill cracks and surface imperfections with patching plaster or a suitable filler. Any gaps resulting from structural movement should be filled with a flexible gap sealant. Sand to a smooth finish as required. Ensure the level of finish is suitable for the coating sheen level and level of critical light – if a higher gloss is used in a harsh critical light environment then prepare to a level 5 finish.

CLEAN









Ensure surface is clean and free from dust. Dust off thoroughly with a damp cloth to remove loosely adhering jointing compound or cornice cement.

PRIME

Prime the substrate with a suitable primer.

Coating System Summary

- | | |
|------------|---|
| • 1st Coat | Dulux 1 Step Prep Water Based Primer Sealer Undercoat |
| • 2nd Coat | Dulux Ceiling White +Plus Kitchen & Bathroom |
| • 3rd Coat | Dulux Ceiling White +Plus Kitchen & Bathroom |

Coating System			
1st Coat — Dulux 1 Step Prep Water Based Primer Sealer Undercoat			
Coat Type 1st Coat	Datasheet NZDU00432 Dulux 1 Step Prep Water Based Primer Sealer Undercoat		
Read the full Datasheet details at Dulux 1 Step Prep Water Based Primer Sealer Undercoat			
Application Methods			
 Air Spray  Airless Spray  Brush  Roller			
	Min	Max	Recommended
Theoretical Spread Rate (m²/L)	<input type="text"/>	<input type="text"/>	14
Wet Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	71
Dry Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	31
Recoat Time **	2 Hours	<input type="text"/>	<input type="text"/>
V.O.C. Level < 40g/L untinted		Meets ECNZ V.O.C. Requirements? Not Applicable	
Coating Application Details Brush, roller, conventional or airless spray. ROLLER: Using a medium nap roller apply a full even coat direct from the container and finish by light parallel strokes with a dry roller. Stir contents thoroughly before and during use. AIRLESS/CONVENTIONAL SPRAY: Suitable for application by all standard spray equipment. If necessary thin with up to 100ml per litre of water to aid atomisation. BRUSH: Wet brushes with water prior to use to avoid clogging. Apply a full even coat direct from the container. When painting exterior surfaces, ensure topcoat is applied no more than one week after application.			
SDS Number DLXNZLEN002997		SDS Link View SDS Link	
2nd Coat — Dulux Ceiling White +Plus Kitchen & Bathroom			
Coat Type 2nd Coat	Datasheet NZDU00448 Dulux Ceiling White +Plus Kitchen & Bathroom		
Read the full Datasheet details at Dulux Ceiling White +Plus Kitchen & Bathroom			
Application Methods			
 Air Spray  Airless Spray  Brush  Roller			
	Min	Max	Recommended
Theoretical Spread Rate (m²/L)	<input type="text"/>	<input type="text"/>	12
Wet Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	83
Dry Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	36
Recoat Time **	2 hours	Indefinite	<input type="text"/>
V.O.C. Level <50 g/L		Meets ECNZ V.O.C. Requirements? Not Applicable	

<p>Coating Application Details</p> <p>Brush, roller, conventional and airless spray.</p> <p>Stir contents thoroughly before and during use with a broad flat stirrer using an upward lifting action.</p> <p>Brush/Roller: Apply full even coats direct from container. If necessary, thin with up to 50 ml water per litre to assist application. Avoid rolling back over nearly dried sections.</p> <p>Airless/Conventional Spray: Suitable for application by all standard spray equipment. Up to 50 ml water per litre may be added to aid atomisation.</p>	
<p>SDS Number</p> <p>DLXNZLEN002618</p>	<p>SDS Link</p> <p>View SDS Link</p>

3rd Coat — Dulux Ceiling White +Plus Kitchen & Bathroom

<p>Coat Type</p> <p>3rd Coat</p>	<p>Datasheet</p> <p>NZDU00448 Dulux Ceiling White +Plus Kitchen & Bathroom</p>
---	---

Read the full Datasheet details at [Dulux Ceiling White +Plus Kitchen & Bathroom](#)

Application Methods



	Min	Max	Recommended
Theoretical Spread Rate (m ² /L)	<input type="text"/>	<input type="text"/>	12
Wet Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	83
Dry Film Per Coat (microns)	<input type="text"/>	<input type="text"/>	36
Recoat Time **	2 hours	Indefinite	<input type="text"/>

<p>V.O.C. Level</p> <p><50 g/L</p>	<p>Meets ECNZ V.O.C. Requirements?</p> <p>Not Applicable</p>
--	---

<p>Coating Application Details</p> <p>Brush, roller, conventional and airless spray.</p> <p>Stir contents thoroughly before and during use with a broad flat stirrer using an upward lifting action.</p> <p>Brush/Roller: Apply full even coats direct from container. If necessary, thin with up to 50 ml water per litre to assist application. Avoid rolling back over nearly dried sections.</p> <p>Airless/Conventional Spray: Suitable for application by all standard spray equipment. Up to 50 ml water per litre may be added to aid atomisation.</p>	
<p>SDS Number</p> <p>DLXNZLEN002618</p>	<p>SDS Link</p> <p>View SDS Link</p>

Coating System Notes

* Practical Spreading Rate will vary from the quoted Theoretical Spreading Rate due to factors such as method and condition of application and surface roughness. ** Recoat times are quotes for 25°C and 50% relative humidity, these may vary under different conditions.

Disclaimer

This Specification is copyright to DuluxGroup (Australia) Pty Ltd and/or DuluxGroup (New Zealand) Pty Ltd (collectively, 'Dulux'). It may not be varied or altered without the prior written consent of Dulux, and if it is, Dulux has no responsibility or liability for those variations.

Unless Dulux has provided you with a customised, project-specific specification, this Duspec+ document does not represent that any particular product or product system will be suitable for your project.

Any information provided in this Duspec+ is given in good faith and is believed by Dulux to be correct at the time of publication. Products and coating systems can be expected to perform as indicated in this Duspec+ document, provided the substrate is in good condition, the coatings are applied by a suitably experienced and skilled applicator, and the preparation, application and maintenance is followed strictly as set out in this Duspec+ document, and as recommended on the applicable Dulux Product Data Sheet and Safety Data Sheets for the relevant products (available from www.duspecplus.co.nz). Climatic conditions at application time can affect Duspec+ documentation suitability and product performance.

The correct colour or colour match is the responsibility of the applicator. Colours will change over time and Dulux does not guarantee that the same colour newly mixed will match a colour applied earlier which has been subjected to weathering or other change elements. No product colour is guaranteed against colour change.

Where any liability of Dulux in respect of this Specification cannot by law be excluded, Dulux's liability is limited, as permitted by law and at Dulux's option, to resupply of the relevant products or services or to reimbursing the cost of those products or services.

WHERE LEAD MAY BE PRESENT: The asset manager is responsible for verifying the presence of lead and determining whether to remove or encapsulate the lead. If lead is present, the work must be done in strict accordance with AS/ NZS 4361 Parts 1 and 2 and Worksafe Australia or New Zealand guidelines.